

# **TECHNICAL DATA SHEET**

## AeroMarine Products ZIP ME-301S

#### **Product Description**

ZIP ME-301S is silicone free and is an excellent release for silicone to silicone applications. It works very well with tin and platinum based silicones. It is stable up to 350°F (177°C). and will provide long lasting release properties under this temperature. This mold release is a FDA and USDA approved liquid petrolatum. It is colorless and non-staining. A light coating produces the best results. **Over application of the mold release may cause inhibition in the silicone.** 

### **Key Features**

- Excellent release for silicone to silicone applications
- Works with tin and platinum based silicones
- Stable up to 350°F (177°C)
- Provides long lasting release properties at or below 350°F
- FDA and USDA approved liquid petrolatum

### **Main Applications**

Silicone to Silicone

### Directions

Shake well. Hold can 8-10 inches from mold. Apply a thin coat. Use a synthetic bristle paintbrush to brush the mold release into finely detailed parts once it has been sprayed on. For best results, do not over-spray.

**DISCLAIMER**: AeroMarine Products makes no warranties, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose. User is responsible for determining whether the seller's product is fit for a particular purpose and suitable for a user's particular method of application. Many factors can affect the use and performance of seller's product. Given the variety of factors that can affect the use and performance of seller's product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the seller's product to determine whether it is fit for a particular purpose and is suitable for the user's method of application. If the seller's product is proven to be defective, THE EXCLUSIVE REMEDY, AT SELLER'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE PRODUCT. Seller shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.